

BOAT LINE

AQUALINE PLUS





Antifouling for propellers

CODE 65-9..

DESCRIPTION AND USE

Insoluble matrix antifouling, copper protoxide free, designed for the protection of propellers, axles and stern drives. Excellent antifouling properties and high-speed resistance.

APPLICATION DATA

3h DRY TO TOUCH	12h HARD DRY	min 8h RECOAT TIME	10m² THEORETICAL COVERAGE 7m² PRACTICAL COVERAGE				 THINNER 7
---------------------------	------------------------	------------------------------	---	--	---	--	---

TECHNICAL DATA

COMPOSITION	Based on special acrylic polymers, natural resins and copper thiocyanate
SPECIFIC GRAVITY	1.50±0.05 Kg/L
AVERAGE VISCOSITY	(Ford Cup No. 4 at 21°C): 130"
FILM THICKNESS	Dry: 52 – Wet: 100 (µm)
FINENESS OF GRIND	30 µm
SOLIDS BY VOLUME	52±3%
V.O.C. % BY WEIGHT	27.98
FLASH POINT	>21°C
MIXING RATIO BY VOLUME	-
POT-LIFE	-
COLOURS	00 white – 18 grey "Volvo" – 40 black
PACKAGING	ml 375
STORAGE	Store in a cool, dry place with adequate ventilation

This product does not contain organotine biocides and complies with the International Convention on the Control of Harmful Antifouling System on Ships adopted by IMO on October 2001 (Document IMO AFS/CONF/26).

PAINT SYSTEM

Surface preparation: Remove all traces of encrustation, dirt and grease. Roughen the surface to help adhesion.

Apply one coat of Aqualine Primer make sure no to apply the paint too thick. After two hours apply one coat of Aqualine Plus. After 24 hours apply a second coat of Aqualine Plus and let dry.

We suggest waiting at least 48 hours before immersion.

CONDITIONS FOR APPLICATION

Apply at a temperature between 5°C and 35°C. Do not apply when the surface temperature is below 3°at dew point.

INSTRUCTIONS FOR USE

Stir well before use.

The technical data are based on a a reference temperature of 20°C unless otherwise specified and refer to the product undiluted and ready-to-use.

We suggest waiting at least 24 hours before launch.

The product is ready to use.

SAFETY PRECAUTIONS

Wear appropriate personal protective equipment; use safety equipment; use with adequate ventilation. For additional safety information, please see the packaging.

This version supersedes any prior version.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.

If products are not used beyond our control our liability is limited to the quality of the product itself.