

CLASSIC LINE

ATTUALITÀ

Exterior gloss enamel

CODE 06-...


DESCRIPTION AND USE

High quality gloss enamel, made of special elements, providing high-resistance against atmospheric agents.

It can be used for the most common surfaces. We suggest using the product for doors and windows, banisters and metal carpentry.

Aspect of the dry film: gloss

APPLICATION DATA

2 h DRY TO TOUCH	18 h RECOAT TIME	12m²/l SPREAD RATE	 READY TO USE
----------------------------	----------------------------	---	---

TECHNICAL DATA

COMPOSITION	Made of alkyd resins dissolved in solvent, titanium dioxide and light-resistant pigments
SPECIFIC GRAVITY	1.200 ± 0.020 Kg/L
FLASH POINT	Over 21°C
SOLIDS BY VOLUME	55%
V.O.C	384 g/L
AVERAGE VISCOSITY	220 Sec (Ford Cup no. 4 at 21°C)
FILM THICKNESS	Dry: 30 Wet: 55 (µm)
FINENESS OF GRIND	5 microns
COLOURS	Colour card – Tingo
PACKAGING	2500 ml – 750 ml – 375 ml
STORAGE	Keep from freezing. Store in a cool and dry place with adequate ventilation

Revision No. 2 dated February 2009

APPLICATION GUIDE

SEE TINS

Thoroughly clean the surface paying attention to remove all grease, dirt, loose paint or rust. Fill holes with plaster and sand if necessary.

Prime the surface with appropriate primers: anti rust primer for iron, matte primer for wood, Zincogum Plus for glass reinforced plastic (GRP), light alloys, copper, stainless steel, PVC etc. Apply one or two coats of Attualità.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.