

CLASSIC LINE



**BRIMAR**  
Special Enamel

CODE 52-2...

**DESCRIPTION AND USE**

Alkyd-based enamel for interiors and exteriors. Its main performance features are ease of application, excellent adhesion, expansion, high covering ability and brilliance.  
Aspect of the dry film: gloss

**APPLICATION DATA**

|                            |                            |   |  |  |
|----------------------------|----------------------------|---|--|--|
| <b>2 h</b><br>DRY TO TOUCH | <b>24 h</b><br>RECOAT TIME | <b>10m<sup>2</sup>/l</b><br>SPREAD RATE | <br>READY TO USE | <br>READY TO USE |
|----------------------------|----------------------------|---|--|--|

**TECHNICAL DATA**

|                          |  |
|--------------------------|--|
| <b>COMPOSITION</b>       | Made of alkyd resins dissolved in solvent, titanium dioxide and resistant pigments |
| <b>SPECIFIC GRAVITY</b>  | 1.500 ± 0.020 kg/L   |
| <b>FLASH POINT</b>       | Over 21°C  |
| <b>SOLIDS BY VOLUME</b>  | 46%  |
| <b>V.O.C.</b>            | 396 g/L  |
| <b>AVERAGE VISCOSITY</b> | 160 Sec (Ford Cup No. 4 at 21°C)   |
| <b>FILM THICKNESS</b>    | Dry: 40 Wet: 90 (µm)   |
| <b>FINENESS OF GRIND</b> | 5 microns  |
| <b>COLOURS</b>           | Colour card  |
| <b>PACKAGING</b>         | 2500 ml – 750 ml– 375 ml   |
| <b>STORAGE</b>           | Keep from freezing. Store in a cool, dry place with adequate ventilation           |

Revision No. 3 dated February 2009

## **APPLICATION GUIDE**

See tin

The surface must be clean free of any oil, dirt, loose paint and rust. Sand and fill holes with plaster if necessary.

Prime the surface with appropriate primers: anti rust primer for iron, matte primer for wood, Zincogum Plus for glass reinforced plastic, light alloys, copper, stainless steel, PVC, etc.  
Apply one or two coats of Brimar

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.  
If products are not used beyond our control our liability is limited to the quality of the product itself.