

PROFESSIONAL LINE

CAPSULA FINITURA

Special coating for the encapsulation
of asbestos-cement surfaces

CODE 44-000

DESCRIPTION AND USE

Special coating with high specific thickness for the interior or exterior encapsulation of new or old asbestos-cement articles.

Aspect of the dry film: satin

APPLICATION DATA

2 h DRY TO TOUCH	18 h RECOAT TIME	2 m²/l FINAL SYSTEM SPREAD RATE (350µm)		 max 5%v/v	 max 5%v/v	 10%v/v	AIRLESS Ø 0.015"-0.021" pressure: 150 atm
----------------------------	----------------------------	--	--	---	--	--	--

TECHNICAL DATA

COMPOSITION	Acrylic copolymers modified in water dispersion, high resistant pigments and special additives.
SPECIFIC GRAVITY	1.400 ± 0.030 Kg/L
FLASH POINT	Not flammable
SOLIDS BY VOLUME	50%
V.O.C.	55 g/L
AVERAGE VISCOSITY	(Brookfield rot. no. 3 at 2rpm at 21°C): 200 Poises
FILM THICKNESS	Dry: 350 – Wet: 700 two coats (µm)
FINENESS OF GRIND	25 microns
COLOURS	White – cement gray – brick red - green
PACKAGING	14000 ml –4000 ml
STORAGE	Keep from freezing. Store in a cool, dry place with adequate ventilation.

This product is supplied with a certificate of conformity released by Istituto Politecnico Giordano
No. 138687 dated 07/07/2000.

Revision No. 2 dated February 2009

PAINT SYSTEM

After the surface is clean, free of dust and grease, apply one basecoat of Capsula Primer.
Do not apply on level surface with water stagnation.

For brush, roller and airless applications, the product is ready to use. (At low temperatures the product must be thinned with max 5% water. For conventional spray painting the product must be thinned with max 10% water.

In order to achieve a dry film thickness of 350 microns with airless spray equipment apply two consecutive coats of product. For roller, brush or conventional spray painting apply 3-4 consecutive coats.

It is very important to achieve a final dry film thickness of 350 microns in order to guarantee an effective "inertisation" of asbestos-cement surfaces in every kind of atmospheric exposure (industrial, marine or rural).

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.
If products are not used beyond our control our liability is limited to the quality of the product itself.