

PROFESSIONAL LINE

# CAPSULA TEMPORANEO

Temporary consolidating primer  
for asbestos-cement surfaces






CODE 44-200

**DESCRIPTION AND USE**

Temporary primer for degraded asbestos-cement surfaces; it can be normally used on friable substrates (plates, false ceilings etc.) before they are removed and disposed of in authorized dumps.

Aspect of the dry film: transparent light red

**TECHNICAL DATA**

<b>1 h</b> DRY TO TOUCH	<b>2-4 m<sup>2</sup></b> SPREAD RATE				 conventional	 airless	<b>AIRLESS</b> Ø 0.015"-0.021" pressure: 150 atm
----------------------------	---	---	---	---	--	--	--

**APPLICATION DATA**

<b>COMPOSITION</b>	Vinyl-versatate resins in water dispersion and special additives.
<b>SPECIFIC GRAVITY</b>	1.000 kg/L
<b>FLASH POINT</b>	Not flammable
<b>SOLIDS BY VOLUME</b>	16%
<b>V.O.C.</b>	< 30 g/L
<b>AVERAGE VISCOSITY</b>	(Ford Cup no. 4 at 21°C): 20 sec
<b>FILM THICKNESS</b>	Dry*: 40 / 80 – Wet: 250 / 500 (µm)
<b>PACKAGING</b>	20000 ml – 5000 ml
<b>STORAGE</b>	Keep from freezing. Keep in a cool and dry place. Do not apply below 5°C and over 35°C.

\* The value above-mentioned is theoretical and it depends on the substrate absorption. It is absolutely necessary to carry out the applications with minimum 15 micron of dry film.

Revision No. 0 dated February 2009

**Capsula Temporaneo has to be considered as the type “D” (auxiliary) in accordance with the Ministerial Decree 20/08/1999.**

**This product is supplied with a certificate of suitability released by Istituto Politecnico Giordano No. 118942 dated 29/06/1998.**

## **PAINT SYSTEM**

Shake the product before use.

Do not clean the surface in order to avoid air dispersion of asbestos fibres. Apply one spray (airless or conventional) coat directly over the surface to work on. Brush or roller can be also used. It is important to respect the practical spreading rate to obtain a good final result.

Under normal temperature and humidity conditions, the items can be removed and disposed of after about two hours since the last application.

If rain is imminent, we suggest not applying the product or protecting the substrate immediately after the application to guarantee final consolidation.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.