

CLASSIC LINE

CENTOExtra-washable and extra-covering
acrylic water-based paint

CODE 00-5...

DESCRIPTION AND USE

Extra washable water-based acrylic paint for interior and exterior surfaces, characterized by excellent coverage (dry or wet).

Aspect of the dry film: flat

Performance features:

- High expansion
- Ease of application
- Velvet finish

APPLICATION

1 h DRY TO TOUCH	min 4h RECOAT TIME	9m²/L SPREAD RATE 2 COATS	 40-50% V/V 2 COATS STANDARD FINISH	 60-70% V/V 3-4 COATS LACQUER FINISH	 30% v/v	
----------------------------	------------------------------	---	---	--	--	---

TECHNICAL DATA

COMPOSITION	Acrylic polymers modified in water dispersion, titanium dioxide, selected charges and extenders.
SPECIFIC GRAVITY	1.530 ± 0.030 Kg/L
FLASH POINT	Not flammable
SOLIDS BY VOLUME	38%
V.O.C.	< 30 g/L
AVERAGE VISCOSITY	(Brookfield rot. No. 4 at 2rpm at 21°C): 450 Poises
FILM THICKNESS:	Dry: 40 – Wet: 125 two coats (µm)
FINENESS OF GRIND	10 microns
COLOURS	White – TINGO – Selezione Interni
PACKAGING	14000 ml – 4000 ml
STORAGE	Keep from freezing. Store in a cool, dry place with adequate ventilation.

WARNINGS:

- Keep from freezing
- Wash the tools with water after use
- Store in a dry place away from sunlight

APPLICATION GUIDE:

Surface must be clean and dry.

- **New walls:** apply one brush coat of Supernovità. Wait at least 4 hours before applying two coats of Cento.
- **Walls already painted:**
 - With washable water-based paint: fill holes with plaster and sand if necessary; clean the wall with a damp sponge and apply one brush coat of Supernovità only on patche areas. Wait at least 4 hours and apply two coats of Cento.
 - With distemper, lime paint or chalking paint: fill holes with plaster and sand if necessary; clean the wall with a damp sponge and apply one brush coat of Supernovità over the whole surface. Wait at least 4 hours before applying two coats of Cento.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.