

CLASSIC LINE

SCUDO

Quartz paint




CODE 48-...

DESCRIPTION AND USE

Quartz coating with very fine granulometry for the protection and decoration of interior and exterior walls and plasters. It is characterized by ease of application, good coverage and resistance against atmospheric agents.

Aspect of the dry film: matt

APPLICATION DATA

2 h DRY TO TOUCH	12 h RECOAT TIME	5 m²/l SPREAD RATE 2 coats on civil plasters		 30%v/v	 20%v/v
----------------------------	----------------------------	--	---	---	--

TECHNICAL DATA

COMPOSITION	based on vinyl-versatate copolymers in water dispersion, titanium dioxide, fine quartz sands and additives
SPECIFIC GRAVITY	1.600±0.030 Kg/L
FLASH POINT	Not flammable
SOLIDS BY VOLUME	57%
V.O.C	< 40 g/L
AVERAGE VISCOSITY	700 Poises (Brookfield rot. no.4 at 2 Rpm at 21°C)
FILM THICKNES	Dry: 130 – Wet: 220 on 2 coats (µm)
COLOURS	White – TINGO – Selezione Architettura
PACKAGING	14000 ml – 4000 ml

Revision No. 0 dated February 2009

WARNINGS:

- Keep from freezing
- Do not apply in the sunlight and when temperature is below 5°C.
- Protect from rain in the days following application
- Clean the tools with water after use
- Store in a dry place away from sunlight

INSTRUCTION AND USE

- **New walls**
After curing (30-40 days) apply one brush coat of Isolante a solvente P.P. or Fissativo Acrilico (diluted 1:4 with water). Wait at least 12 hours and apply two coats of Scudo.
- **Walls to repaint**
 - **Unpainted degraded walls:** thoroughly brush with a wire brush. Clean with water or low pressure washer and let dry. Apply one brush coat of Isolante a Solvente P.P. or Fissativo Acrilico (diluted 1:4 with water). After 12 hours apply two coats of Scudo.
 - **Walls with old paint and loose plasters:** remove all flaky areas and brush with a wire brush. Clean with water or low pressure washer and let dry. Restore the removed areas with hydraulic mortar or ready-mixed concrete. Let the surface cure for at least 10 days. Apply one brush coat of Fissativo Acrilico (diluted 1:5 with water), only over restored areas or also over the whole surface if it needs consolidating. Wait at least 12 hours and apply two coats of Scudo.
 - **Walls with old paint in good conditions:** clean with water or low-pressure washer and let dry. Apply two coats of Scudo.
If the surface needs consolidating, apply one brush coat of Fissativo Acrilico (diluted 1:6 with water).

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.