

CLASSIC LINE

SIGILLO BIANCO

Interior and exterior extra-washable water paint





CODE 00-8..

DESCRIPTION AND USE

Extra-washable water based paint for interior and exterior use. It gives high quality protection and decoration to all kinds of surfaces.

Aspect of the dry film: flat

APPLICATION DATA

1h DRY TO TOUCH	min 4h RECOAT TIME	9 m²/l SPREAD RATE 2 coats on TRIMMED WALL	 40-50% v/v 2 COATS	 60-70% v/v 3-4 COATS	 40% v/v	
---------------------------	------------------------------	--	---	---	--	--

TECHNICAL DATA

COMPOSITION	Vinyl-versatate copolymer in water dispersion, titanium dioxide and extenders
SPECIFIC GRAVITY	1.450±0.030 Kg/L
FLASH POINT	Not flammable
SOLIDS BY VOLUME	32%
V.O.C.	< 30 g/L
AVERAGE VISCOSITY	(Brookfield rot. no.3 at 2rpm at 21°C): 325 Poises
FILM THICKNESS	Dry: 40 – Wet: 125 on two coats (µm)
FINENESS OF GRIND	10 microns
COLOURS	White – TINGO – Selezione Interni
PACKAGING	14000 ml – 4000 ml
STORAGE	Keep from freezing. Store in a cool, dry place with adequate ventilation.

Revision No. 0 dated February 2009

WARNINGS:

- Keep from freezing
- Clean the tools with water after use
- Store in a dry place away from sunlight

APPLICATION GUIDE:

Surface must be clean and dry.

- **New walls:** apply one brush coat of Supernovità. Wait at least 4 hours and apply two coats of Sigillo Bianco.
- **Walls already painted:**
 - With washable water paint: fill holes with plaster and sand if necessary; clean the wall with a damp sponge and apply one brush coat of Supernovità only over patched areas. Wait at least 4 hours and apply two coats of Sigillo Bianco
 - With distemper, lime paint or chalking paint: fill holes with plaster and sand if necessary; clean the wall with a damp sponge and apply one brush coat of Supernovità over the whole surface. Wait at least 4 hours and apply two coats of Sigillo Bianco.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.