

CLASSIC LINE

SOFFIO

Matt enamel


CODE 16-1..

DESCRIPTION AND USE

Alkyd based matte enamel for interiors and exteriors. Its main performance features are ease of application, bright white, high coverage and expansion.

Aspect of the dry film: satin

APPLICATION DATA

| | | | |
|----------------------------|---------------------------|--|--|
| 2 h DRY TO TOUCH | 18h RECOAT TIME | 11 m²/l SPREAD RATE |  READY TO USE |
|----------------------------|---------------------------|--|--|

TECHNICAL DATA

| | |
|--------------------------|---|
| COMPOSITION | Based on alkyd resins, titanium dioxide and flattening agents |
| SPECIFIC GRAVITY | 1.280 ± 0.030 Kg/L |
| FLASH POINT | Over 21°C |
| SOLIDS BY VOLUME | 53% |
| V.O.C. | 395 g/L |
| AVERAGE VISCOSITY | (Ford no. 4 Cup at 21°C): 160 Sec |
| FILM THICKNESS | Dry: 35 Wet: 65 (µm) |
| FINENESS OF GRIND | 2 microns |
| COLOURS | White -black |
| PACKAGING | 2500 ml – 750 ml – 375 ml |
| STORAGE | Keep from freezing. Store in a cool, dry place with adequate ventilation. |

APPLICATION GUIDE

Thoroughly clean the surface removing all grease, dirt, loose paint and rust; fill holes with plaster and sand if necessary. Prime the surface with appropriate primer: anti-rust primer for iron, matt primer for wood, Zincogum Plus for glassfibers reinforced plastic (GFP), light alloys, copper, stainless steel, PVC, etc. Apply one or two coats of Soffio.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.