

BOAT LINE

ANCORPLAST





Single pack grip primer for fiberglass

CODE 72-800

DESCRIPTION AND USE

Product based on phenoxy resin with an excellent adhesion and designed for use on different kinds of plastic surfaces. One single coat over hulls and surfaces over the waterline. Perfect adhesion for the subsequent coats of paint.

APPLICATION DATA

1h DRY TO TOUCH	6h HARD DRY	min 2h max 72h RECOAT TIME	135ml THEORETICAL COVERAGE 95ml PRACTICAL COVERAGE				 THINNER 17
---------------------------	-----------------------	--	---	--	--	--	--

TECHNICAL DATA

COMPOSITION	Based on phenoxy polymers
SPECIFIC GRAVITY	1.20±0.05 Kg/L
AVERAGE VISCOSITY	(Ford Cup No. 4 at 21°C): 40"
FILM THICKNESS	Dry: 15 – Wet: 75 (µm)
FINENESS OF GRIND	30 µm
SOLIDS BY VOLUME	20±3%
V.O.C. % BY WEIGHT	57.30
FLASH POINT	<21°C
MIXING RATIO BY VOLUME	-
POT-LIFE	-
COLOURS	Light green
PACKAGING	ml 2500 – ml 750
STORAGE	Store in a cool, dry place with adequate ventilation

PAINT SYSTEM

Fiberglass reinforced plastic (new)

Surface preparation: Clean and degrease the gelcoat from releasing agents used in the moulds and abrade the gel coat with fine abrasive paper.

Bottom

Apply one thin coat of Ancorplast and finish with two coats of antifouling coating.

Topside

Apply one thin coat of Ancorplast and finish with two coats of Top One.

CONDITIONS FOR APPLICATION

Apply at a temperature between 5°C and 35°C. Do not apply when the surface temperature is below 3°C at dew point.

INSTRUCTIONS FOR USE

Stir well before use.

The technical data are based on a reference temperature of 20°C unless otherwise specified and refer to the product undiluted and ready-to-use.

The product is ready to use.

SAFETY PRECAUTIONS

Wear appropriate personal protective equipment; use safety equipment; use with adequate ventilation. For additional safety information, please see the packaging.

This version supersedes any prior version.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.

If products are not used beyond our control our liability is limited to the quality of the product itself.