

BOAT LINE

BENAR MARINE



Glossy varnish for precious woods

CODE 15-600

DESCRIPTION AND USE

Tropical wood varnish, water and weathering resistant. Its long-lasting flexibility provides an excellent protection for all kinds of woods. For use on exterior and interior wood surfaces above the waterline. Do not apply over timber previously coated with lacquer finish.

APPLICATION DATA

6h DRY TO TOUCH	24h HARD DRY	min 24h RECOAT TIME	18m ^l THEORETICAL COVERAGE 125m ^l PRACTICAL COVERAGE		 THINNER 7
-----------------------	-----------------	---------------------------	---	--	---

TECHNICAL DATA

COMPOSITION	Based on urethane alky resins and UV filters
SPECIFIC GRAVITY	0.90±0.05 Kg/L
AVERAGE VISCOSITY	(Ford Cup No. 4 at 21°C): 65"
FILM THICKNESS	Dry: 35 – Wet: 55 (µm)
FINENESS OF GRIND	-
SOLIDS BY VOLUME	62±3%
V.O.C. % BY WEIGHT	34.44
FLASH POINT	>21°C
MIXING RATIO BY VOLUME	-
POT-LIFE	-
COLOURS	Colorless
PACKAGING	ml 2500 – ml 750
STORAGE	Store in a cool, dry place with adequate ventilation

PAINT SYSTEM

Timber (new)

Surface preparation: Sandpaper and dust. Foreign matters such as glues, grease, etc. must be completely removed as they affect timber priming and cause adhesion problems. Make sure the timber is dry before starting the application.

Apply one coat of Benar Marine diluted with up to 15% Thinner N° 7. If the substrate has a strong absorption, apply a second coat of product diluted with 10% Thinner N° 7. Apply two or three coats of undiluted Benar Marine. For a perfect finish, we suggest sanding with fine abrasive paper between coats.

N.B. For timber priming, refer to the primers of the Cottage Line.

Timber (maintainance)

Surface preparation: Thoroughly sand the surface.

Apply two coats of undiluted Benar Marine.

CONDITIONS FOR APPLICATION

Apply at a temperature between 5°C and 35°C. Do not apply when the surface temperature is below 3°C at dew point.

INSTRUCTIONS FOR USE

Stir well before use.

The technical data are based on a reference temperature of 20°C unless otherwise specified and refer to the product undiluted and ready-to-use.

The product is ready to use.

SAFETY PRECAUTIONS

Wear appropriate personal protective equipment; use safety equipment; use with adequate ventilation. For additional safety information, please see the packaging.

This version supersedes any prior version.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself.