

MARINE LINE

NELSON FLATTING





Transparent glossy varnish

CODE 15-150

DESCRIPTION AND USE

Top quality transparent glossy varnish with strong resistance to marine environment. It enhances the beauty of precious wood and preserve its brilliance and flexibility in time. Aspect of the dry film: glossy.

APPLICATION DATA

4h DRY TO TOUCH	24h HARD DRY	min 20h RECOAT TIME	11 ml THEORETICAL COVERAGE 8 ml PRACTICAL COVERAGE			 1st coat max15% v/v THINNER 7	 2nd coat
---------------------------	------------------------	-------------------------------	---	--	---	---	--

TECHNICAL DATA

COMPOSITION	Based on special alkyd resins with phenolic modification
SPECIFIC GRAVITY	0.90±0.05 Kg/L
AVERAGE VISCOSITY	(Gardner at 21°C): 3.5 Poise
FILM THICKNESS	Dry: 35 Wet: 70 (µm)
FINENESS OF GRIND	-
SOLIDS BY VOLUME	51±3%
V.O.C. % BY WEIGHT	47.34
FLASH POINT	>21°C
MIXING RATIO BY VOLUME	-
POT-LIFE	-
COLOURS	Colorless
PACKAGING	ml 2500 – ml 750 – ml 375
STORAGE	Store in a cool, dry place with adequate ventilation

PAINT SYSTEM

Timber (new)

Surface preparation: Sand and dust. Since foreign materials such as glues, grease etc. affect timber priming and cause adhesion problems, they must be completely removed. Make sure the timber is dry before starting the application.

Apply one coat of Nelson Flatting diluted with 15% Thinner N° 7. If the surface has a strong absorption, apply a second coat of product diluted with 10% Thinner N°7 and then apply two or three coats of undiluted Nelson Flatting. In order to obtain a perfect finish we suggest sanding with fine abrasive paper between coats.

NB For timber priming, refer to the primers of the Cottage Line.

Timber (maintainance)

Surface preparation: Thoroughly sand the surface.

Apply two coats of undiluted Nelson Flatting.

CONDITIONS FOR APPLICATION

Apply at a temperature between 5°C and 35°C. Do not apply when the surface temperature is below 3°C at dew point.

INSTRUCTIONS FOR USE

Stir well before use.

The technical data are based on a reference temperature of 20°C unless otherwise specified and refer to the product undiluted and ready-to-use.

The product is ready to use.

SAFETY PRECAUTIONS

Wear appropriate personal protective equipment; use safety equipment; use with adequate ventilation. For additional safety information, please see the package label.

This version supersedes any prior version.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.

If products are not used beyond our control our liability is limited to the quality of the product itself.