

CLASSIC LINE

**PRIMER 90**





Nitroresistant antirust primer

CODE 11-026

**DESCRIPTION AND USE**

Antirust protective coating, easy to use and fast drying. Its formula contains synthetic resins and anticorrosive pigments for the protection of surfaces in residential applications  
Aspect of the dry film: flat

**APPLICATION DATA**

<b>1h</b> DRY TO TOUCH	<b>4h</b> RECOAT TIME	<b>9m<sup>2</sup></b> SPREAD RATE	 THINNER No.7 or THINNER NITRO	 5% v/v	 READY TO USE	 15% v/v	<b>AIRLESS</b> Ø 0.018"-0.024" pressure: 160 atm
---------------------------	--------------------------	--------------------------------------	---	---	---	--	--

**TECHNICAL DATA**

<b>COMPOSITION</b>	Based on alkyd resins dissolved in solvent, pigments and extenders
<b>SPECIFIC GRAVITY</b>	1.590 ± 0.030 Kg/L
<b>FLASH POINT</b>	Over 21°C
<b>SOLIDS BY VOLUME</b>	59%
<b>V.O.C.</b>	< 500 g/L
<b>AVERAGE VISCOSITY</b>	125 Sec (Ford Cup no. 4 at 21°C)
<b>FILM THICKNESS</b>	Dry: 45 – Wet: 75
<b>FINENESS OF GRIND</b>	30-35 microns
<b>COLOURS</b>	Gray
<b>PACKAGING</b>	18000 ml – 2500 ml
<b>STORAGE</b>	Keep from freezing. Store in a cool, dry place with adequate ventilation.

## APPLICATION GUIDE

- **Unpainted surfaces:** remove all loose mill scale and flaky rust with a wire brush or emery cloth. Clean the surface thoroughly and apply two coats of Primer 90.
- **Previously painted surfaces:** remove all loose paint and flaky rust. Sand the entire surface, clean it thoroughly and apply one or two coats of Primer 90 on damaged areas.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.  
If products are not used beyond our control our liability is limited to the quality of the product itself