

CLASSIC LINE

SIDEROS



Corrosion-resistant antirust coating

CODE 50-0..

DESCRIPTION AND USE

High quality anti-rust coating, with specific properties for the passivation of ferrous metals. It is suitable to protect iron handiworks and pipes and to maintain residential and industrial plants.
Aspect of the dry film: satin

APPLICATION DATA

1,5h DRY TO TOUCH	24h RECOAT TIME	10 m²/l SPREAD RATE	 READY TO USE	 READY TO USE
-----------------------------	---------------------------	--	---	---

TECHNICAL DATA

COMPOSITION	Based on modified alkyd resins, corrosion resistant pigments and selected extenders
SPECIFIC GRAVITY	1.400 ± 0.030 Kg/L
FLASH POINT	Over 21°C
SOLIDS BY VOLUME	53%
V.O.C.	< 500 g/L
AVERAGE VISCOSITY	2.2 Poises (Cone/Plate at 20°C)
FILM THICKNESS	Dry: 40 – Wet: 80
FINENESS OF GRIND	15 microns
COLOURS	Minium (Red lead) – Gray
PACKAGING	2500 ml – 750 ml – 375 ml – 125 ml (only minium)
STORAGE	Keep from freezing. Store in a cool, dry place with adequate ventilation.

APPLICATION GUIDE

- **Unpainted walls:** remove all loose mill scale (calamine) and rust with a wire brush or emery cloth. Clean the surface and check it is completely dry before applying two coats of Sideros.
- **Painted walls:** remove all rust and flaky paint. Thoroughly sand, clean the whole surface and apply one or two coats of Sideros on damaged areas.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.
If products are not used beyond our control our liability is limited to the quality of the product itself