

BOAT LINE

TEAK OIL

Oil for teak wood

CODE 15-900

DESCRIPTION AND USE

Vegetal oil, designed to protect decks in teak wood from oxidation and against the common problems caused by atmospheric agents. It can also be used for different types of wood.

APPLICATION DATA

1h DRYTO TOUCH

min 1h RECOAT TIME

14m/j THEORETICAL COVERAGE 10m/l PRACTICAL COVERAGE







TECHNICAL DATA

COMPOSITION	Based on vegetal oil
SPECIFIC GRAVITY	0.86±0.05 Kg/L
AVERAGE VISCOSITY	(Gardner at 21℃): 0.5 Poise
FILM THICKNESS	-
FINENESS OF GRIND	-
SOLIDS BY VOLUME	20±3%
V.O.C. % BY WEIGHT	76.98
FLASH POINT	>21℃
MIXING RATIO BY VOLUME	-
POT-LIFE	
COLOURS	Straw yellow
PACKAGING	ml 500
STORAGE	Store in a cool, dry place with adequate ventilation





PAINT SYSTEM

Surface preparation: Clean the surface with Wood Cleaner (thinned or undiluted according to the conditions of wood). Surface must be completely dry.

Apply Teak Oil uniformly over the surface with a soft bristle brush following the natural pattern of wood grain. Let it work for 15 minutes and then remove the exceeding oil with a cloth. Allow to dry for at least one hour. Should be timber very deteriorated, apply a second coat of product.

N.B. In presence of damaged seam sealers, we suggest a preventive test in order to avoid an excessive absorption of oil and a consequent possible loosening.

CONDITIONS FOR APPLICATION

Apply at a temperature of 5℃ and 35°. Do not apply under direct sunlight.

INSTRUCTIONS FOR USE

Stir well before use.

The values of technical data are determined at 20°C unless otherwise indicated.

The product is undiluted and ready to use.

SAFETY PRECAUTIONS

Wear appropriate personal protective equipment; use safety equipment; use with adequate ventilation. For additional safety information, please see the package label.

This version supersedes any prior version.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.

If products are not used beyond our control our liability is limited to the quality of the product itself.

62 Revisione N°2 del 19/01/2009