

COTTAGE LINE

VERNICE ALL'ACQUANon flaky, UV resistant
Acrylic finish

CODE 12-7..

DESCRIPTION AND USE

Gloss and satin transparent varnish. Designed for the protection of interior and exterior woodworks. Its main features are: UV resistance, non yellowing properties, ease of application and excellent expansion.

Thanks to its flexibility, the film obtained will follow wood natural grain and will wear out without flaking.

Aspect of the dry film: colourless, gloss or satin

APPLICATION DATA

1h DRY TO	6h RE-COAT TIME	8m²/l SPREAD RATE 1 COAT	 max 5% v/v	 max 5% v/v	 max 15%v/v	
---------------------	------------------------------	---	---	---	--	---

TECHNICAL DATA

COMPOSITION	Based on acrylic co-polymers modified in water dispersion, waxes, UV filters and special additives.
SPECIFIC GRAVITY	1.000±0.030 g/L
FLASH POINT	Not flammable
SOLIDS BY VOLUME	35%
V.O.C.	< 130 g/L
AVERAGE VISCOSITY	200 Sec : (Ford Cup no. 4 at 21°C)
FILM THICKNESS	Dry: 30 – Wet 85 (µm)
COLOURS	Colourless
PACKAGING	ml 2500 – ml 750
STORAGE	Keep from freezing. Store in a cool, dry place with adequate ventilation.

Revision No. 2 dated February 2009

PAINT SYSTEM

Shake well before use.

Do not apply below 5°C and over 35°C.

Do not apply on wet wood.

Do not apply when rain is imminent

Clean the tools with water after use

- **New wood:** thoroughly prepare the surface, sand and remove all dust, grease, wax and silicones. Apply one or two coats of coloured or colourless Impregnante all'acqua and then two or more coats of Vernice all'acqua of the colour desired. For a best result we suggest lightly sanding (use 400 grit wet sandpaper) the surface after the application of the first coat of Vernice all'acqua.
- **Painted wood:** sand old flaky paint and apply two or more coats of Vernice all'acqua.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only.
If products are not used beyond our control our liability is limited to the quality of the product itself.